



Coarse 4"-3/16"

SIZE: 4" - 3/16" Special sizes available. DOT, ASTM & AASHTO
#1, #357, #4, #476, #56, #57, #6, #67, #7, #8, #89

Approvals: - State and Federal

Nebraska Department of Roads	Type B
Iowa DOT	Class D/E
Army Corp of Engineers	
Minnesota DOT	Class III

Typical Physical Properties

Absorption1.66 - 1.84	Freeze-Thaw0.2 - 0.5
LA Abrasion28.5% - 34.1%	ASR0.038% - 0.047%
Deleterious Material Total0.0% - 0.8%	Soundness	
Chert0.0% - 0.7%	Magnesium6.7% - 8.1%
Clay0.0% - 0.3%	Sodium2.3% - 0.047%

Typical Chemical Analysis

CaCO ₃48.2% - 51.8%	SiO ₂4.9% - 7.3%
CaO27.0% - 28.97%	Al ₂ O ₃0.54% - 0.58%
MgCO ₃41.5% - 43.3%	Fe ₂ O ₃0.75% - 1.16%
MgO19.8% - 20.7%	S0.017%

Typical Applications

- Railroad Sub Ballast
- Asphalt
- Concrete
- Construction Entrance Roads
- Driveways
- MSE Wall Backfill
- Runoff Water Containment
- Sediment Check Dams
- Slope Stability
- Other Special Applications

Disclaimer

WARNING: This material contains crystalline silica, which can cause silicosis and lung cancer. See our SDS for additional information.